TECHNICAL REPORT STANDARD TITLE PAGE

1. Report No.	2. Government Accession No. 3. Recipient's Catalog No.				
FAA-AM-77-9					
4. Title and Subtitle	5. Report Date				
INHALATION TOXICOLOGY: I.					
TEST SYSTEM; II. DETERMIN	ATION OF THE RELATIVE TOXIC	6 Pariamina O			
HAZARDS OF 75 AIRCRAFT CAB	o. Performing Organization Code				
7. Author(s) Charles R. Crane, P	h.D.; Donald C. Sanders.	8. Performing Organization Report No.			
M.S.; Boyd R. Endecott, B.					
and Paul W. Smith, Ph.D.					
🤼 Performing Organization Name and Addres	S	10. Work Unit No.			
FAA Civil Aeromedical Inst	itute				
P.O. Box 25082		11. Contract or Grant No.			
Oklahoma City, Oklahoma 7	3125				
		13. Type of Report and Period Covered			
12. Sponsoring Agency Name and Address		OAM Report			
Office of Aviation Medicin	ıe	October 1974 to			
Federal Aviation Administr	ation	September 1976			
800 Independence Avenue, S	S.W.	14. Sponsoring Agency Code			
Washington, D.C. 20591	-				
15. Supplementary Notes					
This research was conducted	ed under Office of Aviation	Medicine Task AM-A-76-TOX-29			
	th support from, Systems Rese	arch and Development Service,			
ARD-500-75-1.					
16. Abstract					
	ne cause of increased safety	I			
	paper presents a detailed d	-			
		s small animals to evaluate			
	of combustion products gene	**			
1		a discussion of the concepts			
	etailed instructions for fab				
	<u> </u>	a test; an evaluation of the			
		75 aircraft cabin materials;			
		r expressing relative toxicity;			
		dose" concept that promises			
to be more useful than "le	ethal concentrations."				
		•			
	·				
17. Key Words Inhalation Toxico	18. Distribution State	em en f			
Combustion Toxicology; Pyro.	— — ·	available to the public			
Time-to-incapacitation; Time	·	National Technical			
Cyanide Toxicity; Aircraft		Service, Springfield,			
Materials; Relative Toxic Ha					
Exposure System; Effective		ر جسے سال محل محل محل محل محل محل محل محل محل مح			
19. Security Classif. (of this report)	20. Security Classif. (of this page)	21. No. of Pages 22. Price			
Unclassified	Unclassified				

ACKNOWLEDGEMENTS

The authors wish to acknowledge the special contributions from the following: Charles Gassaway for design and construction assistance with many details of the exposure system; Charles Trent and F. E. Anderson for fabrication of plastic components and general machine-shop work; Earl Folk, Peter Nelson, and Rosalie Melton, CAMI Biostatistical Unit, for advice and assistance with a myriad of statistical and data-handling problems; G. D. Hanneman, D.V.M., for his expertise and efficiency in securing and caring for a continual stream of healthy experimental animals; Ted Goulden, CAMI Librarian, for invaluable assistance in the never-ending quest for "just one more literature search"; and William Kirkham, Ph.D., M.D., Paula Grape, and Lorrenza Snyder for post-exposure care and observation of surviving experimental animals in addition to all postmortem procedures.

TABLE OF CONTENTS PageIntroduction System Design and Construction ______ Materials ______ A. Animals B. Test Materials C. Combustion Furnace D. Exposure Chamber ______ E. Ventilation System F. Gas Analysis System _____5 IV. Test Procedure Discussion of Results A. Panels B. Panel Components C. Foams D. Fabrics E. Coated Fabrics F. Flooring G. Thermoplastics ______ H. Cargo Liners I. Transparencies ______ J. Insulations K. Elastomers Summary and Conclusions ______ Appendix A. Description and Operation of Exposure Chamber B. Description of the 75 Test Materials C. Tabulated Test Data D. Discussion of the Dose-Response Relationship ____ References LIST OF FIGURES PageFigure 1. Diagrammatic representation of combustionexposure-test system ______ 2. Animal response times for all tested materials ______ 3. Animal response times—panels ______ 4. Animal response times—panel components ______ 5. Animal response times—foams ______

6. Animal response times—fabrics ______

7. Animal response times—coated fabrics ______

8. Animal response times—flooring ______

LIST OF FIGURES—(Continued)	
Figure	
9. Animal response times—thermoplastics	
10. Animal response times—cargo liners	
11. Animal response times—transparencies	
12. Animal response times—insulation	<u></u> _
13. Animal response times—elastomers	
A-1. Animal exposure assembly	
A-2. Animal exposure chamber, end view	
A- 3. Animal exposure chamber, left side	
A-4. Animal exposure chamber, right side	
A- 5. Animal exposure chamber, top view	
A- 6. Animal exposure chamber, top view with	
blower and fan installed	
A-7. Detail section, gas deflector assembly, side view	
A- 8. Rotating cage assembly, side view	m-7 44=
A- 9. Rotating cage assembly, end view	
A-10. Recirculating blower assembly, bottom and side views	·
A-11. Recirculating blower assembly, front view	
A-12. Fan assembly $$	
A-13. Mixing blower with rotor	
A-14. Detail, mixing blower delivery tube	-
A-15. Recirculation assembly	
LIST OF TABLES	
Table	
1. Abbreviated descriptions of the 75 materials, as they appear is	ín
Figures 3 through 13	
B-1. Complete description of aircraft interior materials	
C-1. Mean animal response times for all materials	
C-2. Toxicological rank-order for all 75 materials, as measured by)V
time to incapacitation	<i>√</i>
C-3. Summary of statistical evaluations for certain elements of ra-	w
data and derived relationships	

INHALATION TOXICOLOGY:

I. DESIGN OF A SMALL-ANIMAL TEST SYSTEM

II. DETERMINATION OF THE RELATIVE TOXIC HAZARDS OF 75 AIRCRAFT CABIN MATERIALS

I. Introduction.

In the period from 1964 to 1974, more than 900 people lost their lives in transport aircraft accidents that involved fire. These fatalities resulted from accidents of two types: (i) an impact-survivable crash followed by fire, or (ii) an in-flight fire that resulted in an accident. However, almost half of these fatalities (48 percent) were judged attributable to the direct effects of the fire itself. It is now recognized that the primary cause of death in most fires is the inhalation of incapacitating or lethal quantities of toxic gases or smoke. This is true whether the fire is in an aircraft cabin, a residential bedroom, or a high-rise commercial building.

Firefighters and other rescue personnel were aware of the toxicity of combustion products long before it was established scientifically. They observed that many unconscious victims or fatalities were found in areas completely untouched by flames. Postmortem studies eventually confirmed that most of these fatalities had inhaled sufficient quantities of carbon monoxide (CO) to produce a lethal level of carboxyhemoglobin (COHb) in the blood.

The capabilities of the forensic pathologist and analytical chemist/toxicologist have now progressed to the point that they can show, under favorable circumstances, that many of the victims who do suffer thermal injuries in a fire are first incapacitated by the toxic gases they inhale. Unable to remove themselves from the oncoming flames, they then acquire their thermal insults. Obviously this sequence would not necessarily apply in an accident in which a liquid-fuel-fed fire has entered the occupied space.

The recent availability of more sophisticated analytical techniques has allowed the further determination that chemical compounds other than CO may contribute significantly to the toxicity of the combustion products of modern nonmetallic materials.

The recognition that hydrogen cyanide (HCN) was a combustion product of nitrogen-containing materials prompted Civil Aeromedical Institute (CAMI) scientists, in 1970, to look for the first time at the HCN level in blood specimens from victims of an aircraft accident involving a post-crash fire. It was definitely established that HCN was present in the blood from several victime at levels greater than normal.* As a consequence of these findings, we undertook a systematic study of the inhalation toxicology of CO and HCN, using experimental laboratory animals, to establish some basic relationships for these two highly toxic gases.

In a series of experiments, 4.5 we determined the inhalation doses, for each gas alone and for mixtures of the two, that would physically incapacitate and that which would kill the albino rat. We also showed that within experimental error the magnitude of each effective dose was identical, on a per-gram-of-body-weight basis, for rats, mice, and humans; thus, we established a rationale for utilizing experimental animals to gain information concerning human inhalation toxicology—at least for these two gases.6

^{*} Forty-seven fatalities resulted from the fire that followed a crash on takeoff of a Capitol International Airways, Inc., DC-8 on November 27, 1970, at Anchorage, Alaska.²

The FAA's concern about the hazards associated with aircraft fires has resulted in regulations that control the flammability characteristics of all nonmetallic material used in the cabins of transport aircraft. The first regulations appeared in 1946, and they have been updated periodically through May 1972. Concern for limiting the amounts of smoke and toxic gases produced by burning materials resulted in the issuing of Notices of Proposed Rulemaking (NPRM) in these areas also. As a consequence, the Aviation Toxicology Laboratory, CAMI, undertook such studies by modifying its research task on known mixtures of pure gases to a program for evaluating the toxic hazard associated with inhalation of all the airborne products produced by thermal degradation of nonmetallic materials.

This report describes the authors' approach to a test procedure suitable for evaluating the relative toxic hazard of combustion products. It details the design and construction of such a system and documents its utility by testing 75 aircraft cabin materials and generating from the resultant data a relative ranking of those materials based on the toxicity of their combustion products to albino rats.

Data contained in this report are derived from one specific set of laboratory test conditions that may not adequately reflect conditions in a large scale, uncontrolled fire. Consequently, the reported data alone do not indicate which of the tested materials would be better or worse for use as cabin furnishings. They also do not reflect what the overall level of safety might be in a cabin constructed of such materials. The study does show, however, that for whatever conditions one might choose to accomplish the thermal degradation of a selection of materials, the relative toxicities, for the rat, of their thermal decomposition products can be easily and reproducibly quantified by the use of such a test system.

II. System Design and Construction.

The following concepts were given primary consideration in the design of the combustion/exposure system:

A. The total volume should be kept to the minimum commensurate with containment of

three rats in separate rotating compartments. The minimal volume is desirable to conserve the quantity of sample material needed for each run, to simplify the problem of insuring rapid and complete mixing of a continuously changing atmosphere, and to facilitate the disassembly and thorough cleaning of the system after each run.

ar

WO

eve

wit

one

Suc

len

we:

tim

W0

10

log

sig

bu

fu

ha

Ve

rea

 \mathbf{of}

it

B-

 \mathbf{m}

be

tli

2i

th

16

al

t(

fi

 \mathbf{O}

- B. Any material wetted by the combustion products should be as inert toward them as would be practical considering cost, availability, and ease of construction.
- C. The heating regimen to which the sample is exposed should be reproducible, of sufficient magnitude to insure complete thermal degradation of all organic components, and of a type that would encompass heat transfer by both conduction and radiation, as does a real fire.
- D. The thermal degradation process should be ventilated sufficiently to maintain an aerobic atmosphere.
- E. The evolved thermal degradation products should be immediately conducted into the animal exposure space by the shortest practical path to minimize loss of volatiles by condensation.
- F. The temperature of the animal exposure chamber should never reach a value that would significantly compromise the animal response times.
- G. Oxygen concentration in the exposure chamber should be maintained above 90 percent of the normal ambient partial pressure.
- H. The maximum duration of an exposure should be: (i) so selected that the metabolic production of carbon dioxide by three surviving animals would not result in a concentration greater than 5 percent; (ii) sufficiently short that any metabolic detoxification of a toxic species would decrease its potential effect by a negligible percentage, (iii) short enough to allow a minimum of six experiments per day per test system, and (iv) long enough, considering the precision with which animal response times could be replicated, to give a minimum of five theoretically non-overlapping response time ranges (for example, 8 min±2 and 12 min±2 would be two unique ranges of 6 to 10 min and 10 to 14 min).

It might be appropriate at this point to clarify a relationship between a test system and the "real world." In the context of an individual trapped, even though only momentarily, in a space filled with smoke and toxic gases generated by a fire, one might feel that even a 10-min exposure to such an environment represents an unrealistically lengthy dwell time. Particularly if the "space" were a burning aircraft, one might feel that the time available for escape or successful rescue would be only a minute or two, certainly not 10 min. As a consequence, it might seem only logical that, in an experimental test system designed to evaluate the toxic properties of combustion gases released from burning aircraft furnishings, the duration of exposure to the hazardous environment be limited also to only a very few minutes in order to be consistent with reality.

Let us examine, however, the real purpose of the laboratory test procedure. The objective is to measure the acute toxicity of a mixture of pyrolysis products from Material A and compare it to the toxicity of the products from Material B-and C, D, etc. If one possessed an instrument into which each of these gas mixtures could be introduced, that would produce for us a "toxicity number" such as 1000 for Material Λ , 910 for Material B, and 1250 for Material C, there would be no problem. We could accept that A is 10 percent better than B, and that C is 25 percent better than A, when equal weights of the three were thermally decomposed. There would be no confusion or concern over the fact that the instrument "spent" 18 seconds performing each gas mixture analysis. There would also be no concern that the significance of the stated relative toxicities might be meaningless because the quantity of toxic gas mixture utilized for the analysis would have no effect on a person if totally inhaled—or likewise even if it were sufficient to prove fatal in 30 seconds. These parameters are no more related to the significance of the analytical results than was the time required for the analysis.

In the present case, possessing no such 18-sec instrument, our instrument-of-second-choice is the albino rat. The basis for the analytical measurement is an observable effect on integrated biological activity; the analytical result is the

duration of the exposure, in units of time, from initiation until the desired biological effect is produced. This interval is the time it takes our "instrument" to make an analysis of the potency of the gas mixture. It is also the quantitative analytical result, analagous to the "toxicity number" output by the first instrument. Like the 18-sec analysis time and the resultant toxicity number from the first instrument, the response time of our "mammalian instrument" has no direct relationship to either escape or survival times in a fire. It is, however, a quantity that is related to toxicity, and by which different gas mixtures can be rated relative to each other, and one whose actual magnitude can be limited moreor-less by the proper choice of other parametric values, to any range desired by the experimentalists that would satisfy the four criteria listed initially.

I. The entire system should be a closed one to minimize the quantity of sample material required for a given animal response time. In contrast to a continuous flow-through system, this approach would also allow any decomposition products that might be produced only over a short interval of time to exert their proper toxic potential relative to those products that are formed at a slower rate and over a longer period.

III. Materials.

- A. Animals. The laboratory albino rat was selected for these studies for the following reasons:
- 1. Convenient size (small enough to work with, large enough to furnish adequate blood and other tissue specimens for pathological workup).
 - 2. Readily available at reasonable cost.
- 3. Significant amount of preexisting toxicological and physiological data available in the literature.
- 4. The expertise of the authors in conducting experiments with this animal species.

All animals were males of Sprague-Dawley origin and were obtained from Charles River Breeding Laboratories, Wilmington, Massachusetts. They were ordered at a weight range of 100 to 120 g and were held in isolation in our facility for 2 wk prior to use. On arrival, approximately 1 rat in 10 was sacrificed and inspected for pulmonary pathology that might

affect its response to inhaled gases. No shipment received during this study had to be rejected for preexisting pathology; however, as a precautionary measure, they were all maintained during the first week of isolation on drinking water that contained 1 oz of sulfathiazole per each 5 gal (approximately 1.5 g/L).*

After the second week the rats were moved from the isolation quarters. Those to be used during 1 day's operation were fasted overnight so that all would be in an equivalent metabolic state. Just prior to use, each animal was weighed and coded with a color mark on the head.

B. Test Materials. The subject materials that were evaluated in this study were supplied by the FAA National Aviation Facilities Experimental Center (NAFEC), Atlantic City, New Jersey. All 75 materials had been previously tested by them^{7,8} and were shown to possess the flammability characteristics required by the Federal Aviation Regulations (FAR)⁹ for their use as transport aircraft cabin materials. Many of the materials may be found in use on current models of the wide-body commercial jet fleet.

The same materials were also the subject of a concurrent NAFEC study in which each material was to be thermally decomposed and the evolved pyrolysis products analyzed for nine toxic gases. A complete description of the materials is included as Appendix B.

Following receipt of the materials from NAFEC they were kept in resealable polyethylene bags. For the 24-hr period preceding testing each material was conditioned in a constant humidity chamber maintained at 50±1 percent relative humidity at room temperature (22°-24° C). The sample specimen was then cut into small pieces; in the case of some of the composite materials and the more dense plastics, a small, powered hobby saw (model 57-2, Dremel Mfg. Co., Racine, Wisc.) was used for this purpose. A 0.75-g aliquot** of these pieces was then

weighed to a 0.1 mg accuracy and placed in the appropriate sample boat for insertion into the furnace.

- C. Combustion Furnace. Our choice for a heat source, based on the considerations described above, was the combustion tube furnace (CTF). The CTF offers the following advantages:
- 1. A combination of radiant and conductive heat transfer.

 \mathbf{e}

 \mathbf{r}

- 2. Simple construction of total combustion system.
- 3. Simple and rapid introduction of test specimens.
 - 4. Ease of sample quantitation.
- 5. Elimination of problems with sample melting and dripping.
- 6. Minimized heat transfer to the animal chamber.

The specific CTF used in this study was a Lindberg model 54231A, with a model 59344 controller, that would accommodate tubes to a maximum diameter of 5.08 cm (2 in). When 2.54-cm (1-in) tubes were used, they were centered concentrically within the heaters by means of aluminum plates mounted at each end of the furnace.

Prior to each test the furnace was preheated to 625° C at the controller's sensing element (free air temperature in the middle of the upper heating element). This resulted in a 600° C temperature at the point of contact between sample boat and test material at the required ventilation rate. The furnace controller would then maintain this temperature within $\pm 1^{\circ}$ C.

The decomposition temperature of 600° C was selected after considerable testing of various heating regimens that ranged from 400° C to 850° C; 600° C is above the final decomposition temperature for all materials in the study, as determined by thermogravimetric analysis (TGA), and represents an environment to which any material in a real fire would be subjected. Also, any material that reaches a temperature of 600° C would have passed through all temperatures between ambient and 600° C.

^{*} Sul-Thi-Zol, Sulfathiazole sodium, Merck Chemical Division, Rahway, New Jersey.

^{**}This weight of sample is a fuel-load/system-volume ratio of 60 mg/L, and was selected experimentally as the quantity that seemed most likely to yield the desired distribution among response times for most of the materials that one might want to test.

D. Exposure Chamber. The animal exposure and testing chamber incorporated those considerations outlined earlier. It is shown diagrammatically in Figure 1 and described in detail in Appendix A. Basically, it is a Plexiglas box containing a three-compartment motor-driven exercise wheel and two fans that accomplish rapid mixing of the chamber atmosphere. One-inch-diameter openings at diagonal corners of one face serve as ports for connecting the exposure and combustion systems with a conduit for continuous recirculation between the two.

he

he

at

ed

st

d

f

S

S




FIGURE 1.—Diagrammatic representation of overall combustion-exposure-analytical system.

Numerous small openings with silicone rubber plugs or septa provide for insertion of thermocouples, withdrawal of atmospheric samples, or introduction of gases from the exterior.

The total volume of the final system is 12.6 L; this includes the volume of the chamber, connecting 2.54-cm (1-in) conduits, and the combustion tubes minus the volumes of all interior solids. The final figure was arrived at by dilution ratios for known volumes of propane that were injected into the closed system, allowed to mix to equilibrium, and then analyzed by gas chromatography.

E. Ventilation System. A continuous recirculation of gases between the exposure-combustion systems served to maintain an oxygenated atmosphere in the zone of active thermal decomposition, move the decomposition products out of the furnace and into the exposure chamber, and dilute and cool these products below their flammable concentrations and flash points.

Experimental investigation of the effects of varying the ventilation rate showed the acceptable limits to be 4 and 7 L/min (Lpm). Below 4 Lpm the oxygen in the combustion zone was depleted significantly and the hot, concentrated gases tended to ignite and/or explode as they left the furnace and mixed with the oxygen diffusing back from the chamber. Above 7 Lpm the rate of heat transfer resulted in a chamber temperature of 40° C in 10 min, which was considered excessive.

We believe a ventilation rate of 6 Lpm is ideal (in our system); however, the tests reported here were accomplished with a flow of 4 Lpm. This slight compromise was desirable in order that related tests being done at NAFEC would correlate with ours, for they found it was impossible to accommodate a flow greater than 4 Lpm through their analytical samplers.*

The controlled ventilation was accomplished in our system with a variable speed blower (SCR-controlled) and a small-diameter orifice mounted inline and downstream from the blower. For details see Appendix A.

F. Gas Analysis System. We felt it was desirable to evaluate the concentration-time course of certain combustion products and of oxygen during each experiment. Therefore, an analytical capability was included in the test system that allowed the periodic measurement of chamber concentrations of CO, HCN, oxygen (O₂), and carbon dioxide (CO₂).

Information concerning the concentrations of CO and HCN was considered important for two reasons: (i) Many investigators feel that these two gases are the most important of the combustion products from a toxic hazard standpoint; (ii) Our previous determination of the inhalation

^{*}They ultimately reduced the ventilation rate even further, and their data¹⁰ were collected at 2 Lpm.

dose of each of these gases that would just result in incapacitation or death would allow us to calculate the resultant inhalation doses and determine whether or not these two gases were solely responsible for the observed animal response times. If they are not, then obviously at least a third component contributed significantly to the total toxicity of the combustion products.*

Gas analyses were accomplished with two gas chromatographs (GC) equipped with automated gas-sampling valves. The sample loops of these valves were continuously purged with a gas stream pumped from the exposure chamber via 3.2-mm Saran tubing, through the sample loops, and back into the chamber. The pump (Fluid Metering, Inc., Oyster Bay, NY) exposed the gases to only ceramic, Teflon, and stainless steel and thus minimized reactive losses. At fixed intervals of time the contents of these sample loops were injected into the GC's and the resultant chromatograms displayed on strip chart recorders. One GC was utilized for the determination of HCN only; the other measured the remaining gases—CO, O₂, and CO₂. Chamber HCN concentrations were measured every 3.8 min; CO and O2 were measured at 1.9-min intervals; CO₂ samples were collected manually in syringes and analyzed after the experiment was completed.

The frequent measurement of the O₂ concentration in the chamber allowed us to make manual additions of a quantity of pure O₂ sufficient to maintain the chamber at better than 90 percent of the normal ambient partial pressure. The GC used for cyanide analyses was a Shimadzu model 3B-F utilizing a 2.1-m x 4-mm glass column of Porapak Q and was equipped with a rubidium sulfate thermionic detector of our own design. Nitrogen was the carrier gas.

The second GC was a Carle model 8000 equipped with a 3.2-mm silica gel column followed by a Molecular Sieve-5A column; helium was the carrier gas. The output signal from a thermistor detector was paralleled to a two-channel strip chart recorder. These two channels were operated at different attenuation levels; one

was selected to give a full-scale presentation for the oxygen concentration in ambient air (the nitrogen peak was allowed to go offscale); the other was adjusted for a full-scale response to the expected CO concentration in the chamber. The second column in the two-channel Carle was a 3.2-mm x 1.83-m Porapak Q column that was used for CO₂ analysis.

 \mathbf{f}

su

lo

bl

Si

in

 \mathbf{e}

G. Maximum Duration of an Exposure. Taking into account the principles outlined in Section II,H., we selected a maximum exposure period of 30 min, at which time the experiment was terminated and any surviving animals were returned to their cages and observed for a period of 14 days.

It was determined experimentally that the CO₂ produced in 30 min by three rats in our system never exceeded a concentration of 5 percent (v/v). With 30 min as a limit, one has no difficulty in completing six experiments per day. Also, using a maximum response time of 30 min provides six response categories, each with a ±3 min range $(3\pm3, 9\pm3, 15\pm3, 21\pm3, and 27\pm3)$ min); it actually provides seven categories if one calls "no response in 30 min" an additional category. Ideally once this maximum exposure time has been selected it would be achieved experimentally by selecting a fuel load to be used for all experiments that gave the best distribution of response times over the entire range of 30 min. To insure this one would have to pretest all materials, possibly at several weights of fuel load. We compromised by pretesting 12 materials that we felt would span the full toxicity range and selected a fuel load of 0.75 g for an enclosed volume of 12.6 liters.

IV. Test Procedure.

The sequence of operations for conducting an exposure experiment was as follows:

Three fasted, male rats were color coded, weighed, and placed in the rotating cage, one to a compartment. The preconditioned, weighed test material was placed in a semicylindrical glass sample boat made by cutting a 600-mm x 18-mm tube along a diameter. The material was positioned in the boat so that it would be in the middle of the hot zone when placed in the preheated furnace.

^{*} A detailed account of the results of the gas analyses, and the conclusions derived therefrom, will be the subject of a subsequent Office of Aviation Medicine Report.

If the material to be tested were one of the foams or the bulky insulations a sample tube was substituted for the sample boat. Since these are low density materials, a 0.7-g sample would fill the combustion tube if it were positioned along a 150-mm length of an open boat. This would block the flow of air. Therefore, all foam samples were cut into 1-cm cubes and packed into a 200-mm length of glass tube (18 mm in diameter).

 0Γ

to

1.

C-

16

e-

1e

el

The insulation materials were packed in the tube around a central 6-mm glass rod. When the rod was withdrawn, just before positioning the sample tube inside the combustion tube, the stiffness of the material maintained the open channel. No channel was required with the foams because they melted down to leave an air passage as soon as they were inserted in the 600° C environment.

The cage was placed in the chamber and connected to the drive motor, then the chamber end plate was bolted in place. All thermocouples, sample lines, and the overhead pressure vent line were inserted through the proper ports. The recirculation tubes were connected together and the mixing fans turned on.

When everything was in place and the three operator-observers were ready, the combustion tube was opened, the sample boat was inserted, the system was reclosed, and a master switch was thrown. This switch turns on everything simultaneously, including a digital elapsed-time indicator and the timing device for operating the automated GC sampling valves.

The personnel activities during the run were: One observed the animals and noted the times-to-incapacitation (t₁) and times-to-death (t_d); one monitored the GC presentation of chamber oxygen concentration, added oxygen to the chamber when necessary, and took syringe samples of the chamber atmosphere for CO₂ analysis; and one monitored the sampling and GC system that measured HCN, and assisted in animal observation.

The time at which visible smoke first appeared at the furnace exit was recorded, as were the time and duration of any visible flames. A record was made of the time at which any convulsions occurred in the animals, their t_i and t_d,

and the volume and time of all oxygen additions to the system.

Temperatures at the eight thermocouples were recorded automatically throughout the experiment on a calibrated multipoint strip chart recorder. This record served as an indication of any heat stress imposed on the animals and also depicted the efficiency of the air-mixing fans.

The beam from an amber-lensed, high-intensity lamp (automotive quartz-halogen fog lamp) could be directed down through the top of the chamber to improve visual observation of the animals if significant quantities of smoke were generated. Under the conditions of this test (i.e., aerobic but nonflaming combustion), most of the materials produced little smoke, and then it persisted for only a few minutes.

If there were survivors after 10 min, the recirculation blower was turned off, the conduit tubes removed from the chamber, the chamber ports stoppered, and the sample boat removed from the furnace.

Observation of the animals continued until all three had become incapacitated, at which time cage rotation was stopped to simplify the task of determining when visible respiration had ceased, which we recorded as the t_d. When the last animal had expired, the two large stoppered ports were opened to room air and a third port was connected to a vacuum source. Room air was pulled through the chamber to flush out the noxious and toxic gases.

The chamber was opened by removing the end plate, and the rotating cage was removed. The animals were immediately turned over to the Pathology Research Unit for collection of blood samples and pathological workup. Any survivors were observed until they succumbed, or for 14 days postexposure, and were then included in the pathology study.

The exposure chamber was removed from the system, all fans were dismounted from the walls, and both the chamber and rotating cage were cleaned in warm soapy water followed by an ethanol bath. All fan blades and impellers were also cleaned with ethanol. The parts were then air dried and reassembled. The system was now ready for another experiment.

The combustion/exposure test was replicated a minimum of three times for the first 65 materials and therefore yielded response times based on a minimum of nine animals. Some of those 65 were tested a fourth or fifth time (12 and 15 animals respectively) if the variation in animal response times exceeded a standard deviation of 1 min. The final 10 materials were tested only twice for a total of six animals each.

We found there were two parameters in the experimental design that could not be quantitatively replicated in all experiments without incurring an undesirable increase in time and cost per test. These two parameters were the body weight of the test animals and the weight of material placed in the furnace. Exact replication of animal weights from test to test, especially for animals utilized during their period of rapid growth, would have entailed an almost daily receipt of animals of closely specified weight range. Weighing material specimens to within 0.5 percent of the same weight each time would have been time consuming and would have increased the risk of obtaining a nonrepresentative aliquot from the parent material, especially where the heterogeneous materials were concerned.

However, we have determined experimentally, at least for the metabolic poisons such as CO, HCN, and hydrogen sulfide (H_2S) , that animal response time (t_r) is a function of body weight. If all other conditions are held constant, t_i and t_d are proportional to the fourth root of body weight and inversely proportional to the toxic gas concentration, (C):

$$t_r = k \text{ (wt)} \frac{1}{4} \text{ C}^{-1}.$$
 (1)

We have also verified that the resulting gas concentration is proportional to the weight of material that is thermally decomposed in the furnace and similarly that animal response times are inversely proportional to this sample weight (within the limits of 0.25–1.0 g of material and 0- to 30-min response times, and under the prescribed test conditions).

These relationships were therefore utilized to circumvent the problems of animal and material sample weights that varied from experiment to experiment. We included animals at any body weight between 125 and 350 g and used material

samples at any weight near 0.75 g that would allow representative sampling. The observed response time was then normalized to that which would have resulted with a 200-g animal and a material sample weight of 1.000 g. This normalized value is referred to as a "standard" response time. (See discussion, Appendix D.)

res

tot

the

effi

six

the

bet

per

the

spe

cen

cat

pos

U,

Some of the composite materials in the test series contained one or more components that were thermally stable; e.g., glass fibers and aluminum metal. These inert materials obviously made no contribution to the final mixture of volatile combustion products; therefore, one might want to exclude their portion of the total weight of a test specimen when making comparisons of potential toxicity on an equal-sampleweight basis. For this reason, we also calculated a third set of response times, normalized for a 200-g animal and a 1-g sample weight, except that the sample weight utilized in the normalization equation is that weight lost during combustion, not the 0.75 g loaded into the furnace. Response times calculated in this fashion are referred to as "loss" ti and td.

V. Discussion of Results.

The observed animal responses for the 75 test materials, as measured in the system we have described, yielded t_i 's that ranged from 1.48 to 19.75 min for 71 of the materials; no incapacitations were observed with the other four materials within the prescribed 30-min exposure period. The observed t_d 's ranged from 3.03 to 24.40 min for 56 materials; no deaths were observed in 30 min for 19 of the materials. These mean, observed response times, along with the two sets of normalized values (standard t_r and loss t_r), are presented in Appendix C, Table C-1, for each of the 75 materials and are arranged in increasing numerical order of the material identification numbers.

The 75 materials are listed by their identification numbers in Table C-2 in the order of shortest to longest response times. The observed response times are listed along with the two corresponding sets of normalized response times. The numerical value of the response time for any material can be found by reference to Table C-1.

The statistical precision with which each of the response times was measured is depicted in Table C-3. For each test material we have listed the total number of experimental animals (N) and the relative standard deviation of the mean (coefficient of variation) calculated for each of the six response times. A majority (65 percent) of these relative standard deviations (RSD) fall between 5 and 15 percent RSD, and almost 40 percent of them are less than 10 percent RSD.*

Figure 2 is a specialized bar graph that depicts the standard t_i and standard t_d for each of the 75

materials, arranged in the sequence of increasing t_i . It is apparent that the series of t_i 's represents a near continuum of values, with no obvious or significant breaks in the pattern; therefore, any attempt to place into separate hazard categories two materials that are adjacent, or possibly even near each other, in the plot would require a most arbitrary division.

An additional observation was that materials within each "end use" category, such as foams, panels, fabrics, thermoplastics, etc., had about the same toxicity ranking. Therefore, an arbitrary division of the total group of materials into good versus bad, acceptable versus unacceptable, good versus better, etc., by drawing a line at a given t_i-value would likely place all the elements of one or more end-use categories into the unacceptable group. It seems more realistic




FIGURE 2.—Animal response times (std. t_r and t_d) for the 71 materials that produced incapacitation in 30 min or less. Bottom of each bar represents t_i ; top of bar represents t_d . Relative toxicities decrease from left to right.

^{*}On the basis of previous work with pure gases and of results from the burning of homogeneous polymeric specimens, we feel that those RSD above 10 to 15 percent are due primarily to lack of homogeneity in replicate specimens and/or nonreproducible thermal decomposition.

to evaluate the merit of a given material relative only to other materials that are candidates for the same functional end-use.

In the series of materials under test, there are 10 separate "functional" categories plus an 11th group composed of the individual components that make up the panel composites; e.g., honeycomb cores, adhesive, fiberglass, epoxy. The relative rank-orders of the members of each of these 11 categories are presented in Figures 3–13. In each case the materials are ranked according to their standard t_i 's (bottom bar) from the most toxic on the left (shortest t_i) to the least toxic on the right (longest t_i). The materials are

identified by their code numbers (see Appendix B) and by an abbreviated description of the material. These abbreviations are identified in Table 1.

A. Panels. Most of the 13 panel assemblies consisted of an aromatic polyamide honeycomb core covered with Fiberglas and differed from each other mainly in the outer-most finish layer. Consequently, one would not expect them to exhibit large differences in toxicity and this was borne out experimentally. Values for standard ti ranged from 2.36 min (material No. 20) to 5.85 min (material No. 12) and increased at a fairly constant rate (Figure 3).

Cable 1. Abbreviated Titles for Materials as used in Figures 3 to 13

Material Number	Abbreviation	Material Number	Abbreviation
1	PVF/EPX-FG/AR HC/EPX-FG	78	ΑΌΑΜΤΌ
2	EPX-FG/AR HC/EPX-FG	70 79	ARAMID Diem in emi
6	PVF/AR FIBER-PHEN	80	PLET URETH
ба	PVF/AR FIBER-PHEN	81	URETHANE
9	AL/AR HC/AL	82	PVC
10	FG-POLYESTER	84	WOOL:PVC 76:24
12	PVF/PLST-GLASS/AR HC	85	PVC/COTTON
14	PVF/AR-EPX/AR HC/EPX-FG	86	ABS-PVC PVC
15	PVF/AR-EPX	88	WOOL
18	PVF FILM	89	PVC/NYLON
20	PVF/EPX-FG/AR HC/EPX-FG/PVF	92	ARAMID
24	EPX-FG/PVC/EPX-FG	93	COTTON
25	PVF/FG-EPX/PVF	95	RAYON .
26	FG-EPX	96	WOOL:PVC 49:51
27	MELAMINE-FG	97	PVC-POLYESTER
28	ALUMINIZED PVF/NYLON	99	PVC-PMMA
32	POLYCARBONATE	100	PVC-ABS
33	WOOL/PLST/LATEX	102	POLYETHYLENE
34 27	WOOL/PLST/LTX/URETH	104	PLST URETH
37	PVF/PHEN-FG/AR HC	107	ABS-PVC
38 30	EPX COATED PHEN-FG	108	FR-PMMA
39 40	EPX COATED PHEN-FG	109	PMMA
40 41	AR HC/PHEN-FG BATT	111	POLYCARBONATE
42	EPX COATED PHEN-FG	112	SILICONE
42 43	PVF	113	PVF/PCARB/PVF
46	PVF/PHEN-FG/AR HC	115a	PHEN-FG
50	PVF/PVC/PHEN-FG/AR HC/EPX-FG	116	POLYCARBONATE
	WOOL/PHEN-FG/AR HC/EPX-FG	117	POLYPHENYLENE OXIDE
56	WOOL/EPX/AL/BALSA	118a	FG-EPX/ASBESTOS
60	PVC/SS/EPX/AR-PHEN HC EPX-FG	123	SILICONE
		127	MODACRYLIC
	PVF/PVC/PHEN-FG/EPX/AR HC	130	COTTON/RAYON
	SIL TREATED PHEN-FG	136	PVC/COTTON
	PVC/PHEN-FG/AR HC/EPX-FG	142	WOOL:NYLON 90:10
_	PVF/PVC/PHEN-FG/AR HC WOOL: NYLON 90:10	143a	PLET URETH
	URETHANE		PLST URETH
	URETHANE	144	PVF/EPX-FG/AR HC/EPX-FG
- -	— TITZTATT		,

One in that could fire situation test of the situation for representated in the situated in the population of the population of the situated in the situated i

these neontriber panel of that the last that the aramid ide in

depict
drawn
t_i's.
of a
no cor
of a

can co
basis o
loss—o
therm
order
toxic,
and P
ing c
toxicit

c.
rapid
or n

One material, No. 12, does exhibit a property that could be worthy of consideration in some fire situation; i.e., no deaths occurred in the 30-min test period. In contrast with material No. 69, which has about the same t_i , the interval of time between incapacitation and death for No. 12 is greater than 25 min compared to less than 2 min for No. 69. The longer t_i - t_d interval would represent an increased survival potential in any fire situation that allowed rescue of an incapacitated individual by someone else, such as a building fire, or an aircraft fire at an airport or in a populated area.

B. Panel Components. Results obtained with these nine materials could indicate the relative contribution to the total toxicity of a composite panel that is made by each of the individual panel components. From Figure 4 it is apparent that there is very little difference between near neighbors in the first seven materials; however, the last two do differ both from the first seven materials and from each other. It would appear that the greatest toxicity is associated with the aramid component, which is an aromatic polyamide in either fiber or honeycomb form.

One must bear in mind that the relationships depicted on the bar graph and the conclusions drawn from them are all based on the "standard" t_i 's. These, in turn, are based on the equivalent of a 1-g fuel load of the finished material, and no corrections are made for that residual portion of a material that does not decompose.

By substituting loss t_i's for standard t_i's, one can compare these same nine components on the basis of response time per gram of sample weight loss—essentially, this corrects for the quantity of thermally stable Fiberglas in the sample. The order of relative toxicities, from most to least toxic, then becomes: 38, 6, 6A, 40, 39, 15, 41, 42, and PVF. Three of the four Fiberglas-containing components move to positions of greater toxicity. The most dramatic shift in toxicity occurs with No. 15, which moves from second place down to sixth place; note that it does not contain any Fiberglas.

C. Foams. As a class, the foams decomposed rapidly under our test conditions, leaving little or no residue. Of the nine foams listed in Figure 5, seven yielded t_i values over a narrow

range (4.29-5.55 min). The remaining two materials, a urethane (No. 80) and a polyester urethane (No. 143c), as well as material No. 86, a polyvinyl chloride (PVC) foam, produced no deaths during the 30-min observation period.

D. Fabrics. Although materials in this category represent a wide variety of chemical compositions, with few exceptions the t_i 's were quite short (Figure 6). A modacrylic drapery fabric, No. 127, gave the shortest t_i (1.15 min) recorded for any of the 75 materials and the t_d was less than 3 min. Eleven of the twelve materials gave t_i values of less than 5 min and the remaining one (No. 81, an untreated PVC upholstery fabric) gave a t_i of 7.57 min.

In addition to producing relatively short t_i's, several of these materials also killed the test animals quite soon after incapacitation. The elapsed time between incapacitation and death was less than 2 min for materials No. 93, 85, 127, and 130. In our experience, a short survival time following incapacitation is usually associated with the presence of supralethal levels of CO.

E. Coated Fabrics. All materials in this group were fabrics that had been coated with PVC. The shortest t_i was 6.97 min for a lightweight, flame retardant-treated polyester (No. 97) used as a seat bottom diaphragm. The remaining materials were heavy upholstery fabrics and yielded t_i's of from 7.47 to 13.71 min (Figure 7).

Two of these materials appear particularly promising from a toxicological standpoint. Materials No. 89 (PVC/nylon) and No. 136 (PVC/cotton) yielded t_i's of 10.70 and 13.71 min respectively, and neither material killed the test animals in the 30-min observation period.

On a sample weight basis, both coated cotton materials (No. 84 and 136) appeared to be less toxic than their uncoated counterpart, material No. 93. However, since the weight ratio of fabric to coating in these materials is not known, it is difficult to know whether the lowered toxicity of the cotton/PVC materials is due (i) to the substitution of a significant part of their total weight with the less toxic PVC or (ii) to changes in the flammability and burning characteristics of the fabric because of the PVC coating.




Figure 3.—Panels. Relative toxicity of combustion products as measured by animal response time. Bottom of each bar represents t_i; top of bar represents t_d. Relative toxicities decrease from left to right.





Figure 4.—Panel components. Relative toxicity of combustion products as measured by animal response time. Bottom of each bar represents t_i; top of bar represents t_d. Relative toxicities decrease from left to right.



5

FIGURE 5.—Foams. Relative toxicity of combustion products as measured by animal response time. Bottom of each bar represents t_i; top of bar represents t_d. Relative toxicities decrease from left to right.




Figure 6.—Fabrics. Relative toxicity of combustion products as measured by animal response time. Bottom of each bar represents t_i; top of bar represents t_d. Relative toxicities decrease from left to right.




Figure 7.—Coated fabrics. Relative toxicity of combustion products as measured by animal response time. Bottom of each bar represents t_i ; top of bar represents t_d . Relative toxicities decrease from left to right.

F. Flooring. The range of t_i's produced by this group of composite materials was from 4.94 min (No. 9) to 10.90 min (No. 24) (Figure 8). For this category, as was the case for the Panel category, one might want to look at the loss t_i values in conjunction with the standard t_i values, for some of the flooring samples also have a non-combustible component. For example, No. 9, an aromatic polyamide honeycomb/aluminum sandwich, exhibits a surprisingly short t_i when one considers that more than 50 percent of its total weight is metallic aluminum.

In general these materials fall into two toxicity levels, with No. 9, 33, and 34 exhibiting t_i values of about 5 min and t_d values of one and one-half to three times the t_i . Materials No. 24 and 52 have t_i 's of approximately 10 min and no observed deaths. Material No. 56 represents a transition between the two groups with a t_i of 7.46 min and a t_d almost twice the t_i value. The last two, No. 24 and 52, would appear to be

superior materials from a purely toxicological viewpoint based on comparisons of equal weights of finished products.

G. Thermoplastics. The thermoplastics constitute most of the molded plastic panels, seat shrouds, etc., found in an aircraft cabin interior. On the basis of their toxicity, these materials fall into two distinct classes and an intermediate group. The polycarbonate materials (No. 32, 11, 116) had t_i's of about 4 min and very short t_i-t_d intervals—less than 2 min between incapacitation and death. All the PVC/ABS materials produced t_i's of approximately 10 min and no deaths, while the remaining materials, a polyphenylene oxide (No. 117) and a PVC/acrylic (No. 99), gave intermediate animal response times.

In our test system all the polycarbonates, as well as the phenylene oxide, produced very high peak CO concentrations. The small differences observed in animal response times may reflect differing thermal stabilities of the respective materials rather than any substantive differences in combustion products.




Figure 8.—Flooring. Relative toxicity of combustion products as measured by animal response time. Bottom of each bar represents t_i ; top of bar represents t_d . Relative toxicities decrease from left to right.




FIGURE 9.—Thermoplastics. Relative toxicity of combustion products as measured by animal response time. Bottom of each bar represents t₁; top of bar represents t_d. Relative toxicities decrease from left to right.

H. Cargo Liners. Materials in this category consisted of Fiberglas-reinforced plastic sheets containing variable quantities of nonflammable material (Figure 10). In general, the observed ti's were related to the quantity of noncombus-




Figure 10.—Cargo liners. Relative toxicity of combustion products as measured by animal response time. Bottom of each bar represents t_i; top of bar represents t_i. Relative toxicities decrease from left to right.

tible material in each sample; i.e., the larger the fraction of thermally stable component, the longer the t_i .

Materials that produced animal incapacitation within the 30-min observation period were a Fiberglas/polyester (No. 10) and two Fiberglas/epoxy sheets (No. 26, 60). Their respective t₁'s were 3.99, 7.68, and 10.33 min. Two materials neither incapacitated nor killed the animals: No. 25, a PVF-coated Fiberglas/epoxy and an asbestos-impregnated Fiberglas/epoxy (No. 118A). The animal survivors from tests of No. 118A were observed for 8 days posttest and were then sacrificed. No obvious ill effects of the potential asbestos exposure were noted during the 8 days, and no gross or microscopic pathology attributable to asbestos was found on postmortem examination.*

^{*}All premortem and postmortem pathology conducted on the animals involved in this entire study was accomplished by William R. Kirkham, Ph.D., M.D., Chief, Pathology Research Unit, Aviation Toxicology Laboratory, Civil Aeromedical Institute. The pathology results will be published as a separate Office of Aviation Medicine Report.

Fig

the:

weig

teria

 \mathbf{For}

alon

 $20~\mathrm{p}$

mos

Car

whe

are

sign

mer

botl

test

toxi

to 1

14.9

capa

abo

K

I. Transparencies. The three materials in this category yielded a wide range of toxicity values. One polycarbonate (No. 111) gave a t_i of 3.80 min; the second acrylic (No. 109) did not incapacitate in 30 min (Figure 11). Material No. 111 gave the rapid production of a very high CO level, which led to the usual short t_i-t_d interval. Material No. 109 provided a surprising, although not completely unexpected, incident in the latter phases of the test series. After the initial tests had confirmed that we were not going to observe a t_i<30 min for some materials, larger samples were loaded to determine what weight would be necessary to obtain an observable incapacitation. The required weight of the larger sample was estimated on the basis of the quantity of CO and HCN resulting from the original decomposition of 0.75 g of material and the knowledge of the incapacitating doses of these gases for the rat. When a calculated incapacitating load of No. 109, 2.25 g, was tested, the mixture of pyrolysis gases generated was sufficiently concentrated, at the ventilation rate of 4 L/min, to produce an explosive mixture in the chamber. These gases were ignited by a flame that originated in the furnace tube, and the resultant explosion severely damaged the exposure chamber. The experience was an excellent demonstration of one of the advantages of a chamber constructed from plexiglas rather than glass, and it prompted us to add a large blowout panel to the design of future chambers.

J. Insulations. Materials from this end-use category that were included in the test series were limited to three Fiberglas insulation batts containing various binders (No. 27, 66, 115A) and a single insulation batt cover material (No. 28) composed of aluminized PVF and nylon (Figure 12). The range of t_i's for the batts was from 3.70 min for a melamine batt (No. 27) to greater than 30 min for a silicone-treated phenolic-Fiberglas batt (No. 66). A nonsiliconed phenolic batt (No. 115A), on the other hand, gave a t_i of 12.26 min. No deaths were observed with any of the four materials.

The Fiberglas content of these materials is about 80 percent (by weight); therefore, the amount of material undergoing decomposition in




Figure 11.—Transparencies. Relative toxicity of combustion products as measured by animal response time. Bottom of each bar represents t_i ; top of bar represents t_d . Relative toxicities decrease from left to right.




Figure 12.—Insulations. Relative toxicity of combustion products as measured by animal response time. Bottom of each har represents t_i ; top of bar represents t_d . Relative toxicities decrease from left to right.

the furnace is only about 20 percent of the loaded weight. It is this small amount of binding material that is responsible for the animal responses. For material No. 27, for instance, if the melamine alone accounts for the t_i of 3.7 min and is only 20 percent of the total weight, then on an equal weight basis, pure melamine would be about the most toxic polymeric material we have tested. Careful consideration should be given to this fact when such materials are used, for although they are light in weight they can still comprise a significant fraction of the total weight of polymeric material used in aircraft.

K. Elastomers. Two door-sealing materials, both of which were silicone elastomers, were tested in the series (Figure 13). From the toxicological standpoint, material No. 123 proved to be the better of the two, producing a t_i of 14.96 min and no deaths. Material No. 112 incapacitated the animals in 9.16 and killed them about 4 min later.




FIGURE 13.—Elastomers. Relative toxicity of combustion products as measured by animal response time. Bottom of each bar represents t₁; top of bar represents t₄. Relative toxicities decrease from left to right.

VI. Summary and Conclusions.

We have described in some detail the concepts, design features, construction, and testing of a small-scale system that utilizes small laboratory animals for evaluating the relative toxicities of combustion products from polymers. Overall system performance was demonstrated by testing 75 materials used in aircraft cabin interiors and ranking them according to their relative inhalation toxicities to the albino rat.

Relative rank-orders for these 75 materials have been presented in several ways:

- A. On the basis of two animal end points: i.e., relative times-to-incapacitation and times-to-death.
- B. On the basis of equal material weights loaded in the furnace.
- C. On the basis of the loss of equal weight of material during pyrolysis.
- D. On the basis of animal response times corrected for differences in animal weights and sample weights.

The significance of the various bases for these multiple rankings has been discussed, as have the relative merits for selecting one base over another for a specific application. We feel that use of either "loss" or "standard" response times is equally valid provided the choice is based on the proper recognition of what each measurement signifies and its relationship to the weight of the material involved. If one were primarily interested in evaluating relative performance of materials as they would be used in an installation, the use of "standard" response times would probably be preferable. However, if one were interested in the potency of the decomposition products, per se, one might choose to look at "loss" response times. For most comparisons, the use of "standard ti" is the one preferred by the authors.

Judging from the distribution of t_i's throughout the 0 to 30-min exposure period, it appears that a more uniform distribution might have resulted with a fuel load slightly less than the 0.75g/12.6 L that was selected.

The system is small (12.6 L), easily constructed by laboratory personnel, and relatively inexpensive to assemble. It will accommodate from 8 to 12 tests per day per unit, utilizing three rats per test, with cleaning between successive tests. For such biological end points, reproducibility of animal response times from test to test is surprisingly good, as is the precision of the measurement from animal to animal within a given test.

The simplicity of design, low cost, ease of operation, and reproducibility of results suggest that the significant features of this system and its operating parameters are worthy of consideration in the current search for a standard system with which to measure the relative inhalation toxic hazards associated with nonmetallic polymeric material.

One must, however, bear in mind that this test system, reproducible as it is and useful as it may be, shares a fault common to all such systems in use or proposed. The parameters of the thermal decomposition process do not necessarily represent, and are not presented as a representation of, the processes that exist in a "real" fire. Therefore, the resultant relative toxicity ranking may not reflect the relative hazards of these or other such materials under actual fire conditions. We consider this to be a preliminary study with the primary objective that of designing a suitable system for making toxicity measurements of gaseous environments, not reproducing actual fire atmospheres. The described system accomplishes that objective surprisingly well. We recommend that additional studies be conducted to refine the parametric values in order that they may more adequately reflect those of significance in a fire.

APPENDIX A

DESCRIPTION OF THE ANIMAL EXPOSURE CHAMBER AND ITS OPERATION

•

APPENDIX A

ANIMAL EXPOSURE ASSEMBLY

I. Chamber Materials and Construction.

All transparent portions of the chamber were constructed from Plexiglas sheets. Inlet and outlet bushings for the combustion tube and recirculation assembly were machined from solid Plexiglas stock. Each was grooved to accept two inset Viton O-rings (Arthur H. Thomas Co., No. 8088-J39, 25-mm i.d. x 3-mm wall thickness). Curved plastic sections for the rotor shrouds on the mixing and recirculating blowers were fabricated from flat Plexiglas stock by heating and bending to shape. All edge and end joints on the chamber were reinforced by drilling, threading, and countersinking three holes per side for flathead 8-32 machine screws approximately 2 cm long. Plexiglas joints were then cemented with No. 3 Plexiglas cement (Cope Plastics, Oklahoma City, Oklahoma).

The bearing for the steel center shaft (axle) was machined from solid Teflon to an internal diameter matching the shaft diameter. The mixing blower rotor was machined from Teflon stock and the rotor for the recirculation blower was cast in a rubber mold from filled epoxy resin.

The combustion tube is a 2.5-cm (o.d.) Vycor tube with a short, graded scal attachment to a Pyrex ball joint (SJ 35/25). The remainder of the recirculation assembly was built from standard Pyrex tubing coupled to SJ 35/25 ground, ball-and-socket assemblies. Sampling ports were turned and drilled from solid Plexiglas stock and covered with red rubber serum bottle stoppers (7-mm plug diameter x 11-mm flange diameter, Arthur H. Thomas Company, No. 8753-D32). Thermocouple inserts were fabricated from copper-constantan wire (24 ga., 0.508-mm diameter, No. GG-T-24, Omega Engineering Company, Stamford, Connecticut) cemented into bored and shortened No. 00 rubber stoppers with a clear silicone rubber sealer (Dow Corning No. 684).

Sealing gaskets for the three fan/blower assemblies were made by squeezing a band of clear silicone rubber sealer onto one of the mating surfaces and allowing it to dry. A gasket for the chamber end plate was formed with the plate clamped lightly in place against 3-mm-thick spacers placed in the chamber thumbscrew holes. Silicone rubber sealer was applied to the end plate. The silicone was prevented from adhering to the chamber end by covering the silicone layer with Teflon tape strips. After the gasket had cured, the Teflon strips were removed.

Two additional thermocouple inlets was drilled into the back plate. One was 6 cm below the center shaft bushing; the other was 3 cm from the side opposite the mixing blower and 3 cm below the top surface. A third thermocouple inlet was drilled in the chamber bottom, centered on the cage compartment next to the end plate (separate drawings for the back plate and bottom are not shown).

The external delivery tube for the mixing blower was constructed (for lack of available tubing) by boring a 2.5-cm-diameter Plexiglas rod to the proper internal diameter, then cutting and cementing as shown in Figure Λ -14.

A flow-limiting orifice for the recirculating assembly was cut from thin plastic to fit the internal diameter of the 35/25 ball joint. A 6-mindiameter hole was drilled in the center of this disc. An orifice of this size allowed flow-rate adjustments to be made over the desired range of values by altering the rpm of the controllable blower motor.

II. System Assembly.

Assembly of the animal exposure system is accomplished by placing the chamber shell on the channel-iron frame and plugging thermocouple assemblies and serum-bottle stoppers in the appropriate outlets. A pressure relief tube

of 2-mm i.d. polyethylene is fitted into a top corner with the distal end extending into the intake of the overhead fume hood. The recirculating and mixing blowers (top) and the mixing fan (side) are attached with screws and tightened until gaskets just form a gas-tight seal (usually finger tight).

The steel drive shaft is inserted through the center of the cage and locked into position by tightening the two set screws. The cage containing the animals is placed in the chamber and the axle is rotated until the set screw on the motor shaft engages the slot on the cage assembly shaft. The motor shaft set screw is tightened. A short length of coiled spring is fitted over the opposite end of the axle to hold the cage assembly against the rear Teflon bushing when the cover is in place. The glass deflector plate is fitted into its holder, the chamber cover bushing is fitted over the cage axle, and the thumbscrews are hand tightened until a seal is effected.

.

The furnace with the combustion tube in place is moved toward the chamber assembly between its aluminum guides until it comes to a stop against a set screw in one of the guides. The combustion tube is then inserted through the chamber cover. The stem of a female 35/25 ball-joint unit is inserted into the outlet of the recirculating blower, the flow-limiting orifice is fitted onto the end of the extension tube ball with a small amount of silicone grease, and the joints are clamped together. The U-tube and thermocouple holder are then clamped into place to provide a continuous recirculation system. The cage motor, temperature recorder, recirculating and mixing blowers, and fan are each plugged into a separate outlet on the outlet strip so that individual switches allow separate component testing and a single master switch provides for simultaneous activation at the beginning of an actual test.

APPENDIX B

DESCRIPTION OF THE 75 AIRCRAFT INTERIOR MATERIALS AND THEIR PHYSICAL PROPERTIES

Table B-1.—Description of Aircraft Materials*

٠.	Chemical Composition	Thickness (in)	Unit Weight (ox/yd ²)	Designation	Cabin Use
1	PVF/Epoxy-Fiberglas/Aramid Honey- comb/Epoxy-Fiberglas	0.388	48.5	Panel	Ceiling panel
2	Epoxy-Fiberglas/Aramid Honeycomb/ Epoxy-Fiberglas (No. 1 without PVF finish)	0.376	39.6	Panel	Celling panel
<u> </u>	PVF/Aramid Fiber-Phenolic	0,048	56.4	Panel component	Face for sidewall or window reveal (upper surface)
4	PVF/Aramid Fiber-Phenolic	0,050	58.4	Panel component	Face for sidewall or window reveal (lower surface)
)	Aluminum/Aramid Honeycomb/	0,371	86.3	Flooring	Floor
)	Fiberglas-Polyeater	0.039	35.1	Cargo liner	Side cargo liner
2	PVF/Polyester-Chopped Glass/ Aramid Honeycomb/Polyester- Chopped Glass	0.525	90.4	Panel	Overhead stowage door assembly
4	PVF/Nomex-Epoxy/Aramid Honey- comb/Epoxy Fiberglas	0.532	49.7	Panel	Acquatic wall panel
	PVF/Aramid-Epoxy (Acoustic Skin for No. 14)	0.015	9.75	Panel component	Face of acoustic wall panel
1	PVF (Clear Film)	0.001	1.11	Panel component	Panel finish
	PVF/Epoxy-Fiberglas/Aramid Honey- comb/Epoxy-Fiberglas/PVF	0.958	82.8	Pane 1	Partition
·	Epoxy-Fiberglas/PVC/Epoxy-Fiberglas	0.410	117	Flooring	Floor
_	PVF/Fiberglas-Epoxy/PVF	0.051	76 .7	Cargo liner	Cargo liner
	Fiberglas-Epoxy	0.013	16.3	Cargo liner	Cargo liner
,	Melamine-Fiberglas	1.19	5.43	Insulation	Fuselage insulation
}	Aluminized PVF/Nylon Scrim	0.007	1,33	Insulation	Cover for insulation batt
2	Polycarbonate	0.054	47.4	Thermoplastic	Molded part
3	Wool Pile/Polyester Backing/Latex Coating	0.265	51.8	Flooring	Carpet
4	Wool Pile/Polyester Backing/Latex Coating/Urethane Pad	0.345	51.3	Flooring	Carpet
7	PVP/Phenolic-Fiberglas Screen/ Aramid Honeycomb filled with Phenolic-Fiberglas Batt/Phenolic- Fiberglas	0.517	77.2	Panel	Center ceiling panel
38	Epoxy Coated Phenolic-Fiberglas (Backing for No. 37)	0.017	18.4	Panel component	Backface of ceiling panel
39	Epoxy Coated Phenolic-Fiberglas (Adhesive used in No. 3/)	0.018	17.6	Panel component	Adheaived used in ceiling panel

^{*} Reproduced directly from the NAFEC report⁸ with the permission of the author.

Table B-1—(Continued)

No.	Chemical Composition	Thickness (in)	Unit Weight (oz/yd ²)	Designation	Cabin Use
40	Aramid Honeycomb filled with Phenolic-Fiberglas Batt (Core for No. 37)	0,451	10.8	Panel component	Ceiling panel core
41	Epoxy Coated Phenolic Fiberglas (Screen used in No. 37)	0.038	15.3	Panel component	Screen used in cell- ing panel
42	PVF (Acoustic Skin for No. 37)	0.015	12.7	Panel component	Ceiling panel finish
43	PVF/Phenolic-Fiberglas Screen/ Aramid Honeycomb/Aramid Honey- comb filled with Phenolic-Fiber- glas Batt/Phenolic-Fiberglas	0.732	85.8	Pane1	Drop ceiling panel
46	PVF/PVC/Phenolic-Fiberglas/ Aramid Honeycomb/Epoxy-Fiberglas	0.500	79.2	Panel	Upper sidewall panel
50	Wool Carpet/Phenolic-Fiberglas/ Aramid Honeycomb/Epoxy-Fiberglas	0.445	95.0	Panel	Lower sidewall panel
52	Wool Carpet/Epoxy Adhesive/Aluminum/ Balsa Wood/Epoxy Adhesive/Aluminum	0.690	198	Flooring	Floor panel
56	PVC/Stainless Steel/Epoxy Adhesive/ Aramid-Phenolic Honeycomb/Epoxy Adhesive/Stainless Steel	0.490	168	Flooring	Floor panel
60	Epoxy-Fiberglas	0.018	22.9	Cargo liner	Cargo liner
61	PVF/PVC/Phenolic-Fiberglas/Epoxy Adhesive/Aramid Honeycomb/Epoxy Adhesive/Phenolic-Fiberglas	0.500	69.1	Panel	Overhead stowage panel
66	Silicone-Treated Phenolic-Fiber- glas	1.38	ن.09	Insulation	Fuselage insulation
67	PVC/Phenolic-Fiberglas/Aramid Honeycomb/Epoxy-Fiberglas	0.273	68.1	Panel	Door liner
69	PVF/PVC/Phenolic-Fiberglas/Aramid Honeycomb/Epoxy-Fiberglas	0.531	93.0	Panel	Door assembly
70	FR Wool (90 percent)/Nylon (10 percent)	0.037	11.3	Fabric	Upholstery
73	PR Urethane	0.500	17.4	Foam	Seat pad
74	FR Urethane	0.500	12.4	Foam	·
78	Aramid	0.046	12.1	Fabric	Seat pad
79	FR Polyether Urethane	0.500	13.7	Foam	Upholstery
30	FR Urethane	0.500	11.3	Foam	Seat cushion
31	PVC (untreated)	0.096	25.3	Fabric	Seat cushion
32	FR Wool (76 percent)/PVC (24 percent)	0.039	12.6	Fabric	Upholatery Upholatery

Table B-1—(Continued)

No.	Chemical Composition	Thickness (in)	Unit Weight (ox/yd ²)	Designation	Cabin Use
84	PVC/Cotton (untreated)	0.058	26.9	Coated fabric	Arm rest cover
85	ABS-PVC (untreated)	0.060	56.4	Thermoplastic	Seat side panels and trays
86	PVC (untreated)	0.500	28.8	Foam	Flotation cushion and padding for seat back and arm rest
88	FR Wool	0.055	17.2	Fabric	Upholstery
89	FR PVC/Nylon	0.059	26.3	Coated fabric	Seat arm cap
92	Aramid	0.036	11.8	Fabric	Upholetery
93	FR Cotton	0.012	3.06	Fabric	Upholstery
95	FR Rayon	0.041	15.4	Fabric	Upholstery
96	Wool (49 percent)/PVC (51 percent)	0.044	13.8	Fabric	Upholstery
97	FR PVC-Polyester	0.018	11.4	Coated fabric	Seat bottom diaphragm
99	FR PVC-Polymethyl Methacrylate	0.044	39.6	Thermoplastic	Seat shroud
100	FR PVC/ABS	0.092	86.9	Thermoplastic	Seat shroud
102	FR Polyethylene (rigid)	0.500	13.7	Foam	Flotation cushion
104	FR Polyester Urethane	0.500	40.1	Foam	Seat cushion
	ABS-PVC	0.127	122	Thermoplastic	Molded part
107	FR Polymethyl Methacrylate	0.054	46,6	Transparency	Scratch Lhield
108	Polymethyl Methacrylate	0.260	228	Transparency	Window, pane
109		0.052	46.2	Transparency	Windscreen
111	Polycarbonate	0.094	86,3	Elastomer	Door seals
112	Silicone	0.431	151	Thermoplastic	
113	PVF/Polycarbonate/PVF	1.09	6.40	Insulation	Puselage insulation
115	Phenolic-Fiberglas Polycarbonate	0.043	36.8	Thermoplastic	Passenger service units and luminaires
117	Polyphenylene Oxide	0.041	31.4	Thermoplastic	Flight station and lavatory parts
1184	Fiberglas-Epoxy/Asbestos	0.020	28.9	Cargo liner	Cargo liner
	Silicone	0.124	116	Elastomer	Door seals
123		0.032	8,63	Fabric	Drapery
127	Modacrylic Conton/Payon	0.040	15.0	Fabric	Upholstery
130	······································	0.057	28.3	Coated fabric	Upholstery
136 142		0.035	10.3	Fabric	Upholatery

Table B-1—(Continued)

No.	Chemical Composition	Thickness (in)	Unit Weight (oz/yd ²)	Designation	Cabin Use
143a	FR Polyether Urethane	0.500	13.9	Foam	Seat cushion
143c	FR Polyester Urethane	0.500	38.8	Foam	Seat cushion
144	PVF/Epoxy-Fiberglas/Aramid Honeycomb/Epoxy-Fiberglas	0.276	43.3	Pane 1	Wall panel

ABBREVIATIONS

ARS - Acrylonitrile/Butadiene/Styrene FR - Flame-retardant treated

PVC - Polyvinyl chloride PVF - Polyvinyl fluoride

APPENDIX C

A TABULATION OF ANIMAL RESPONSE TIMES AND THE RESULTING RELATIVE TOXIC HAZARD FOR THE 75 MATERIALS, AND THE ANALYTICAL PRECISION WITH WHICH RESPONSE TIMES WERE MEASURED, AS REFLECTED BY THE RELATIVE STANDARD DEVIATIONS OF THE MEAN RESPONSE TIMES.

Table C-1. Mean Response Times for Each of the 75 Test Materials

Mean Responsé Time (Minutes)

Material No.	Obse	erved (1)	Stan	dard (2)	Los	Loss		
······································	t ₁	t _d	t _i	t _d	t _i	^t d		
1	3.34	6.99	2.61	5.47	1.64	3.44		
2	4.04	9.69	3.07	7.38	1.76	4.23		
6	6.51	9.29	5.07	7.23	1.97	2.80		
6a	6.68	9.37	5.22	7.31	2.20	3.08		
9	6.61	9.20	4.94	6.88	2.15	2.99		
10			3.99		3.60	5.59		
12	7.57	7.89 	5.85		3.60			
14	3.09	6.89	2.38	5.31	1.80	4.02		
15	5.09	9.05	3.89	6.94	3.74	6.66		
20	3.04	5.77	2.36	4.48	1.66	3.15		
24	14.68	****	10.90		5.37	****		
25								
26	9.95	18.92	7.68	14.61	3.64	6.91		
27					0.69			
28	8.71		6.56	_ _ _	6.24			
32	4.94	6.71	3.70	5.02	3.61	4.90		
33	7.07	15.80	5.26	11.73	4.95	11.07		
34	7.35	20.43	5.53	15.35	5.13	14.26		
37	5.06	7.06	3.90	5.43	2.06	2.87		
38	6.27	11.96	4.79	9.15	1.44	2.75		
39	7.88	16.15	6.09	12.56	2.76	5.69		
40	4.31	8.14	3.22	6.08	2.51	4.74		
41	11.19	24.40	8.36	18.22	4.69	10.24		
42	11.40	19.91	5.82	10.16	4.71	8.24		
43	4.85	7.90	3.70	6.02	2.31	3.76		
46	5.59	9.61	4.18	7.17	2.37	4.04		
50	6.17	9.32	4.70	7.10	3.05	4.62		
52	13.11		9.84		5.45			
56	10.12	17.60	7.46	12.97	4.75	8.26		
60	13.63		10.33		4.37			
61	4.07	7.39	3.07	5.57	2.09	3.79		
66						Marie World		
67	7.33	11.97	5.58	9.15	3.34	5.48		
69	6.49	8.92	4.86	6.68	2.90	3.98		
70	3.66	8.27	2.72	6.16	2.36	5.36		
73	5.59	8.57	4.29	6.59	4.46	6.80		
74	6.61	10.61	5.04	8.08	5.10	8.15		
78	3.04	8.36	2.23	6.13	2.17	5.97		
79	6.35	9.70		7.34	4.74	7.25		
80	9.91	16.37		12.40	7.21	11.82		
81	9.99	19.09		14.45	7.44	14.18		
82	4.72	8.32	3.47	6.12	3.43	6.04		

Table C-1 (continued)

Material No.	Obser	ved	Stand	ard	Los	SS
•	ti	td	ti	t _d	ti	t
84	9.73	17.52	7.47	13.43	6.91	12.46
85	14.22	معمة البيد و الا المسادد معمد مسمد مسمد	10.79		9.97	
86	7.10		5.50	~~ -~~ -~~	4.03	
88	2.70	5.62	2.00	4.17	1.75	3.63
89	14.29		10.70		9.89	
92	2.83	5.55	2.15	4.22	2.00	3.94
93	3.95	•	3.07	4.58	2.74	4.10
95	5.43	7.43		5.72	3.51	4.81
96		13.19		10.18	4.53	9.96
97		13.59		10.28	6.51	9.60
99		11.10		8.44	5.88	8.25
100				— — —	8.49	
102	-	10.26	5.25	8.08	5.55	8.60
104	7.09	11.05	5.55	8.65	5.50	8.57
107			9.59		8.89	
108	10.06	19.75	7.56	14.73	7.50	14.60
109					****	
111	4.98	6.94	3.80	5.28	3.75	5.21
112	12.02	17.95	9.16	13.66	2.26	3.38
113	5.13	7.06	4.04	5.56	3.99	5.49
115a	13.08		12.26		2.98	
116	4.85	6.97	3.83	5.50	3.76	5.40
117	6.87	9.12	5.19	6.89	5.11	6.78
118a						
123	19.75		14.96		2.99	
127	1.48	3.03	1.15	2.34	1.10	2.24
130	3.76	5.46	2.93	4.24	2.72	3.94
136	18.12		13.71		11.87	
142	2.85	6.04	2.22	4.70	2.01	4.26
143a	6.34	9.77	5.06	7.80	5.06	7.80
143c	12.20	SOM describ descrip STAND	9.58		8.43	
144	4.28	7.02	3.19	5.26	1.77	2.92
PVF	17.17	20.33	13.02	15.42	13.19	15.61

- 1. Observed response times are those determined experimentally; they have not been transformed in any way except for calculation of the mean value of all observed times.
- 2. Standard response times are the observed times normalized to those for a "standard" 200-g animal and a "standard" fuel load of 1.000 g rather than the weight actually used.
- 3. Loss response times are the observed times normalized to those for a "standard" 200-g rat and for a loss of fuel weight of 1.000 g rather than the actual weight loss.
- 4. A (----)entry indicates no response during the 30-min observation period.

Table C-2. Materials Ranked in Order of Decreasing Toxic Hazard

Material Numbers Listed by Ranking Criteria

Rank Order	Observed t _i	Standard t _i	Loss t _i	Observed t _d	Standard t _d	Loss t _d
1	127	1.27	27	1.27	127	127
2	88	88	127	130	88	38
3	92	92	38	92	92	6
4	142	142	1	88	130	37
5	78	78	20	20	20	144
6	20	20	88	93	93	9
7	14	14	2	142	142	6a
8	1	1	144	32	32	20
9	70	70	14	14	144	112
10	130	130	6	111	111	1
11	93	93	92	116	14	88
12	2	61	142	1	37	43
13	61	2	37	144	1	61.
14	144	144	61	37	116	92
1.5	40	40	9	113	113	130
16	82	82	78	61	61	69
17	116	27	6a	95	95	14
18	43	43	112	10	43	46
19	27	32	43	43	40	93
20	32	111	70	40	82	2 1/2
21	111	116	46	70	78	142
22	37	1.5	40	82	70	50 40
23	15	37	130	78	10 72	95
24	10	10	93	/ 3 C 0	7 3 6 0	32
25	113	113	39	69 1 =	69 a	111
26	95	95	69	15	117	70
27	73	46	115a	117	15	116
28	46	73	123	6	50	67
29	96	96 50	50 67	50	46	113
30	50	50 20	82	6a	6	10
31	38	38	95	46	6a	39
32	143a	79 60	10	2	79	78
33	79	69 0	12	79	2	82
34	69	フル	32	143a	143a	15
35	6	74 143a	26	102	74	117
36		143a 6	15	74	102	73
37	74		111	104	99	26
38	102	117	116	99	104	79
39	6a	6a 102	113	38	67	143a
40	117	102	J. J. J			

Table C-2 (Continued)

.

• •

Rank Order	Observed t	Standard t _i	Loss t	Observed t _d	Standard t _d	Loss t
41	33	33	86	67	38	7/
42	104	86	60	96	42	74
43	86	34	73	97	96	42
44	67	104	96	33	97	99 56
45	34	67	41	39	33	56 704
46	12	42	42	80	80	104
47	39	12	79	84	39	102
48	99	99	56	56	56	97 06
49	28	39	33	112	84	96 41
50	97	28	143a	26	112	41 22
51	84	97	74	81	81	33 80
52	8 0	56	117	108	26	80 84
53	26	84	34	42	108	81
54	81	80	24	PVF	34	34
55	108	108	52	34	PVF	108
56	56	81	104	41	41	PVF
57	41	26	102	• • • • • • • • • • • • • • • • • • •	··· F _ L	TAT
58	42	41		No animal death	s were noted d	urina
59	112	112	28	the 30-min obse	rvation portod	ar TiiR
60	143c	100	97	for materials No	0.12.24.25	27
61	100	143c ·	84	28, 52, 60, 66,	85 86 89 1	Δ ,
62	107	1.07	80	107, 109, 115a,	118a 123 13	60,
63	11 5 a	52	81	and 143c.	~~~~, <u>~</u> ~~, <u>~</u>	· ,
64	52	60	108			
65	60	89	143c			
66	85	85	100			
67	89	24	107			
68	24	115a	89			
69	PVF*	PVF	85			
70	136	136	136			
71	123	123	PVF			

No animal incapacitation was noted during the 30-min observation period for materials No. 25, 66, 109, and 118a.

Table C-3. Statistical Data. The Relative Standard Deviation of the Means of the Various Measured or Calculated Response Times

			Relative	Standard	Deviations	(%)	
Material		Observed	Response	Standard	Response	Loss	Response
Number	N*	ti	td	ti	td	ti	td
		ר די ד	14.9	16.0	14.2	17.1	15.1
1	9	17.1		8.4	15.2	8.5	15.2
2	6	10.6	16.7 7.9	7.5	8.4	7.2	6.8
6	9	7.0		8.6	6.7	5.3	4.7
6a	9	8.5	7.2	8.8	6.0	10.1	6.4
9	9	9.4	5.7 15.2	15.7	12.6	12.0	
10	9	18.2		11.1		10.6	
1.2	9	11.2	10 /	7.2	11.1	7.3	11.7
14	9	7.5	10.4	7.2 5.4	14.7	5.4	14.7
15	6	3.9	12.0	3.4 8.7	14.7	7.8	<u>-</u>
20	9	9.2	18.0	13.2		11.8	
24	9	14.5		13.2			
25	9		22.2		23.3	14.8	25.8
26	9	8.9		9.3	ر ه ري ــــــــــــــــــــــــــــــــــــ	~ ¬ -	
27	9	16.0				25.2	
28	12	26.1	 7 0		6.4		_
32	12	6.8	7.2	6.1	24.8		
33	9	6.9	25.5		32.0	7.8	
34	9	7.1		8.3	8.7	9.8	
37	9	10.5		11.3	15.3	4.5	
38	6	5.0	13.1	127	41.5		_
39	6	10.6		12.7 13.9	11.7		_
40	6	13.6	9.9		9.6		
41	6	2.9	27 . 4	6.6	27.6		
42	6	6.4		8.1	9.7		
43	9	7.9 17.2	•	14.6	12.2		
46	12	14.3		9.0	3.7		
50	9	9.9		55.5			
52	12	25.2		9.1	21.6		
56	9	9.6					
60	9	11.4 8.8		8.5		9.3	
61	9	0.0					
66	1.5	12.1	11 3	11.3	14.8	11.3	14.7
67	9	7.1		6.6		6.7	<u> </u>
69	9	25.2		25.1	27.7		,
70	12			27.7	31.3		
73 77	12	29.8 22.0	33.1		29.3		
74	1.2		9.6		11.6		
78	9	8.3 16.0	•	12.2	10.6		
79	9	16.9	27.3		22.2	7.0	
80	9	13.9	~ ~ ~ ~ ~ ~ ~ ~ ~ ~ ~ ~ ~ ~ ~ ~ ~ ~ ~	0.2	Fr. 2-1 T 212		

^{*} N = number of animals tested --- = no response during 30-min observation period

Table C-3 (Continued)

-	Material Number N		Relative Standard Deviations (%)					
			Observed Response		Standard Response		Loss Response	
	MOUTHET	TA	t i.	td	ti	td ,	ti	td
	81	9	7.7	23.3	7.7	22.7	7.6	22.3
	82	9	12.4	12.6	12.8	13.2	12.8	13.2
	84	9	9.1	24.5	9.2	23.0	10.1	
	85	9	16.7		15.1		14.1	25.1
	86	12	40.7		38.2		39.9	
	88	9	12.7	13.2	12.3	13.6		
	89	15	19.0		17.4	T.J.O	13.1	14.4
	92	1.2	6.3	27.8	8.1		16.7	~~~
	93	9	15.1	9.6	13.1	27.7		28.3
	95	9	21.3	19.4		9.0	10.9	7.4
	96	9	4.7			12.0	14.4	11.8
	97	9	8.7	22.8	7.8	20.1	6.4	20.9
	99	9		11.2	7.6	11.2	7.1	11.2
	100	9	10.5	8.8	8.8	8.0	9.2	8.1
	102	9	18.3		16.7		16.1	
	104	7 0	12.7	6.0	13.9	6.9	13.9	14.0
	107	ح ا د	13.0		13.8	19.5	13.9	19.5
		15	25.5		23.4		22.9	····
	108	7.0	20.0	32.0	17.2	27.8	17.6	27.8
	109	12						
	111	12	7.5	4.7	8.5	5.6	8.5	5.6
	112	15	11.6	18.2	8.4	15.8	34.4	37.3
	113	9	9.4	10.0	10.1	10.4		10.4
	115a	9	69.2		59.0		57.3	
	116	9	9.6	6.4	7.5	3.7	7.0	3.2
	117	18	13.5	12.4	10.5	9.7	10.0	9.2
	118a	9			***************************************			
	123	6	27.4		28.2		24.4	
	127	9	7.4	9.4	4.7	8.1	6.5	10.3
•	130	9	8.5	9.0	7.0	6.7	7.0	6.5
	136	12	21.0		22.6		23.9	
	142	9	20.4	7.7	21.7	8.2	21.4	9.1
	143a	9	9.5	14.1	9.6	14.1	10.3	14.6
	143c	9	13.2		13.7		13.3	14.0
	144	9	12.0	11.2	10.6	12.7	10.2	
•	PVF	6	18.3	15.6	18.6			14.8
•		Mean RSD:	14.0	$\frac{15.6}{15.6}$	$\frac{13.0}{13.2}$	$\frac{16.1}{15.1}$	$\frac{18.4}{13.4}$	$\frac{15.5}{15.5}$
			· - -		حک ی کب حاد	エン・エ	エン・4	15.5

APPENDIX D

DISCUSSION OF THE BIOLOGICAL PRINCIPLES AND MATHE-MATICAL RELATIONSHIPS PERTINENT TO THE CONCEPT OF A DOSE-RESPONSE RELATIONSHIP IN INHALATION TOXICOLOGY.

.

APPENDIX D

DOSE-RESPONSE RELATIONSHIPS IN INHALATION TOXICOLOGY

In earlier CAMI studies of the toxicology of atmospheres containing CO, HCN, or mixtures of the two, we were faced with an experimental design problem. To properly communicate the nature of this problem and our efforts to solve it, a short digression will be necessary.

In the classical approach to an evaluation of a toxicological dose-response relationship, it is axiomatic that a constant, and known, quantity of the substance under investigation be administered reproducibly to a large number of test animals. These animals must all be as nearly identical as is practical. Repeated administrations over a selected dosage range are then made to additional animals. Results of such investigations may then be expressed as the dosage required to elicit a particular animal response. This dosage is commonly expressed as the quantity of test substance administered per unit of animal body weight. In toxicological terms this effective dose may be referred to as a lethal dose, an hypnotic dose, an incapacitating dose, etc.

All animal experimentation involves one source of variability with which most physical scientists never have to contend, and that is the variability in response from one biological individual to the next, even when presented with identical stimuli. The existence of such a variability therefore requires that each experimental dosage be administered to a sufficiently large population of otherwise identical subjects to attain a statistically reliable response. In classical toxicology this led to the expression of "effective dose" in terms such as ED₅₀, which signifies a dose sufficient to elicit the measured response in exactly 50 percent of the test animals. Obviously other homologous terms are in common usage; examples are: LD_{25} (lethal dose for 25 percent of the test population), ED₉₉, LD₁, etc.

In addition, the biological response may vary both qualitatively and quantitatively according to the route of administration of a given dose. Therefore, if one is to adequately describe a toxicological dose-response relationship, the route of administration must also be specified; e.g., oral LD₅₀, dermal ED₇₅. These dose-response relationships are quite straightforward and logical and present little difficulty for the experimentalist in properly designing and executing most toxicological investigations; that is, unless the route of administration is to be by way of inhalation.

In the case of a gaseous agent, how does one quantitate the dose received by each animal? In these instances, the common approach (historically) has been to express the concentration of the substance under investigation as it exists in the atmosphere to which the animals are exposed, and specify one additional experimental parameter—the time interval over which the exposure took place. The terms corresponding to effective doses thus become effective concentrations, administered for specified times. Examples would be: lethal concentration for 50-percent mortality in a 5-min exposure (5-min LC₅₀) or, similarly, 10-min EC₂₅, etc.

Now, after such a digression, we return to our experimental problem. We were interested in defining the dose-response relationships for the effects of two toxic gases, CO and HCN, on two responses of the albino rat. The responses we chose to measure were physical incapacitation (that is, loss of coordinated psychomotor control) and death (operatively defined as cessation of visible respiration for 20 seconds). We felt that these two responses were the most appropriate for an investigation concerned with the effect of combustion gases on an individual's ability to escape from a fire environment.

The animal exposure chamber designed by the authors for conducting these experiments included four wheel-type cages similar to free-running exercise wheels except that they were driven externally at a constant speed. This feature of the chamber was specifically designed to allow the determination of physical incapacitation. It would also control each animal's physical activity at a constant and reproducible level during an experiment as well as from one experiment to the next.

There were two aspects to the problem, and they became obvious when we tried to expose multiple sets of four animals to identical gas concentrations. We found it extremely difficult to quantitatively reproduce the HCN atmosphere from test to test and also discovered that it was going to be a logistic nightmare (as well as uneconomical) to attempt through a long series of tests to have each rat at the same weight at the time of his exposure.

The inability to control these two factors to the desirable degree meant that both of the elements of dosage (namely, quantity of toxicant inhaled and animal body weight) would have an undesirable amount of statistical variation and thus compromise the utility of these derived values. We therefore decided to evaluate a different approach, one that would allow us to calculate the dose administered to each animal and also circumvent the requirement for using animals at only one weight.

The magnitude of a "dose" acquired by inhalation would be dependent on the following factors:

(i) the respired alveolar volume, (ii) the concentration of the gas in the inspired air, (iii) the efficiency of extraction of that gas from the alveolar space into the blood, and (iv) animal body weight. It seemed to us that each of these parameters could be quantitated, either with certain assumptions or under specified conditions.

The volume of the respired alveolar air could be approximated to the extent that Guyton's relationship¹² held for our experimental conditions. He reported that the correspondence between minute-respiratory-volume and body weight of an albino rat was expressed by the equation:

$$RV(minute) = 2.1 \ (body Wt)^{0.75}$$
. (D1)

Body weight is in grams, the minute-respiratory volume (RV) is in milliliters per minute, and the units of 2.1 are ml min⁻¹ g^{-0.75}. Thus, RV could be easily calculated. Since the gas concentration in the enclosed atmosphere could be measured, and the extraction efficiency was assumed to be unity, the dose could be calculated.

If the toxicological principle of equal doses eliciting equal responses (provided all other pertinent parameters are held constant) were to apply here, then animals of equal weight would all inspire the same total quantity of the toxic constituent before exhibiting the same response—in our case, before becoming incapacitated or by the time of death. Therefore the incapacitating dose for all animals of equal weight should be identical, as should be the lethal dose.

If the effective dose for an animal were divided by that animal's body weight, we should have an "effective dose per gram of body weight." Furthermore, we hypothesized that at least for poisons such as CO and HCN, the ED per gram of body weight should be constant for animals of any weight—with the possible exception of the very young and the very old. We therefore had a relationship that would allow us to make exposures at any concentration to animals of differing body weights and still collect useful data.

The dose equation is derived in the following manner: Quantity of air respired would be the product of the minute-respiratory volume (RV) and the time, in minutes, t:

The total volume of toxic gas respired in time, t, would be the product of the total volume of respired air and the concentration (V/V) of the gas in the air, (C); this would be a dose, d, for the whole animal:

$$d = C (RV) t$$
 (D3)

Dose on a per gram body weight basis would be:

$$D = d(Wt)^{-1} = C(RV) t(Wt)^{-1}$$
. (D4)

If this time, t, is the exposure interval required to bring about the specified response, incapacitation or death, then the dose, D, is respectively the incapacitating dose, D_t , or the lethal dose, D_d . The corresponding times would be time-to-incapacitation, t_i , and time-to-death, t_d .

Substituting Guyton's formula for RV (for the albino rat):

$$D = [C t 2.1 (Wt)^{0.75}] (Wt)^{-1}. (D5)$$

By simplying this equation, we can see how the effective dose is a function of body weight:

$$D=2.1C t (Wt)^{-0.25},$$
 (D6)

where Wt is in grams. Thus dose is inversely related to the fourth root of body weight.

It is obvious that the equations just derived are based on an exposure to a constant concentration of the active material. The relationship is equally valid for a changing concentration, provided one has adequate knowledge of the time-concentration profile over the time interval from t=0 to $t=t_1$ or t_d . The value for the integal (or area under the curve) of the concentration versus time curve, from zero time to the response time, can be entered in the equation as the (C) (t) product. One could also think of this as finding the Ct product, dividing by t to give an average (or effective) concentration (C) over the exposure interval, and entering this as (C) in the original equation.

Exposure of a large number of rats, whose body weights ranged from 100 to 500 g, to various concentrations of CO and HCN has verified that the derived relationship is a useful one. For the level of activity represented by the driven wheel in our exposure chamber, we found the following effective doses for CO and HCN for the albino rat.

For HCN: Incapacitating dose = 0.32 mg/kg Lethal dose = 1.95 mg/kg

For CO: Incapacitating dose=15.35 mg/kg
Lethal dose =50.53 mg/kg

These doses are expressed as the weight of toxic material that must be inhaled per kg body weight to produce a given effect. They may be converted to an equivalent concentration value (concentration of the toxic gas in the atmosphere), and if expressed in (volume/volume) parts per million (ppm), they now represent the "dose" for a given response when the (C) in the equation is expressed in ppm (V/V). These values for D would then be:

D
$$(death) = 45,790 \text{ ppm } (ml/g)$$

Now that the effective doses for either response are known, we can demonstrate one of the very useful features of this relationship that is lacking in the usual expressions of "X-minute ED_y."

If one had a literature value of a 30-min LC₅₀ (or LC₉₉) for a particular gas and for an animal weight of 350 g but was interested in a 5-min lethal concentration for 200-g animals, the literature value is of little use beyond affording one an approximate value from which he might speculate. Using equation (D6), however, the response time for a rat of any weight exposed to any concentration (within the limiting values) can be calculated once D has been determined.

For example, the HCN concentration, maintained at a constant value, that would incapacitate a 200-g rat in 5 min would be (from equation (D4)):

$$C_i$$
 (5 min) = D (WT)/t (RV)
= $(299) (200) / [5(2.1) (200)^{0.75}]$
= 107.1 ppm.

The 5-min lethal concentration would be:

$$C_d$$
 (5 min) = (1834) (200)/[5(2.1) (200)^{0.75}]
=657 ppm.

The time to incapacitation for a 300-g rat exposed to a CO concentration of 15,000 ppm would be:

$$t_i = D(Wt)/[2.1 (C)(Wt)^{0.75}]$$

= $(13,907)(300)/[(2.1)(15,000)(300)^{0.75}]$
= 1.84 min.

The t_d for a 500-g rat, exposed to 10,000 ppm CO, would be 10.3 min.

These four calculations indicate the increased utility of such a relationship.

We have independently evaluated the accuracy of the lethal cyanide dose as calculated from our inhalation experiments. At the same time we have confirmed our belief that the extraction of HCN from alveolar air into blood would be essentially 100 percent efficient. (This belief was based on the known physical and chemical properties of HCN and the conditions under which alveolar exchange takes place.)

Since the results of our inhalation experiments yielded a calculated lethal cyanide dose for rats of 1.95 mg/kg, we decided to give a series of rats a graded dosage schedule of CN- by direct intra-

venous (i.v.) injection and compare lethal doses. A solution of buffered NaCN was injected into the exposed femoral vein of an ether-anesthetized rat; his heart action was monitored by palpation and his respiration was observed visually. Animals receiving doses of CN-, based on individual body weights, that were from 50 percent to 90 percent of the lethal *inhalation* dose (1.95 mg/kg) survived the administration, while those receiving 100 percent to 200 percent of the lethal inhalation dose succumbed.

In most of the animals, we observed rather dramatic responses immediately following the injection. In particular, respiration was erratic with varying periods of apnea. Cardiac activity also became erratic at the higher doses and, in the case of the nonsurvivors, continued long after respiration had terminated.

(An interesting sidelight to this experiment that illustrates the reversibility of the observed, intermittent periods of apnea occurred with the animal that received 90 percent of the lethal dose. Because this animal had experienced a prolonged period of apnea, our attending pathologist pronounced it dead when cardiac activity could no longer be felt; so it was placed in a plastic bag on top of the other carcasses—the 90-percent dose was the last experiment of the day. The plastic bag was placed in a freezer overnight, as the animal caretaker who handled disposal had left for the day. In the morning, on retrieving the bag for disposal, there sat the "90-percent animal" on top of its deceased and frozen litter mates. Except for frostbitten (or frozen) nose, ears, toes and tail, it seemed none the worse for its "cyanotic" ordeal. We mention this primarily because it may suggest that the use of some degree of hypothermia could have value in the treatment of near-fatal cyanide poisonings.)

This correspondence between the values for lethal dose, as determined from inhalation experiments and by direct i.v. injection, supports the validity of the inhalation data and verifies that the efficiency of HCN extraction from alveolar space into blood approaches 100 percent.

Alveolar extraction efficiencies for CO are approximately 50 percent until the blood carboxy, hemoglobin (COHb) level reaches 40-percent to 50-percent saturation. Above this COHb level, the extraction efficiency for CO will decline. However, in our treatment of the dose-response relationship, we chose to define dose as the quantity of the toxic agent that is inspired and to ignore any fractional portion that may not be absorbed and would therefore be exhaled. In other words, for the purpose of calculating what we define as dose, we arbitrarily assume that the extraction efficiency is 100 percent.

We have also found that dose-response relationships measured in the above fashion may b_e of use in extrapolating data from one animal species to another, provided the minute-respiratory volumes are available or can be suitably estimated. As an example, using a literature value for the 5-min LC₉₉ for mice exposed to CO, we have converted this concentration figure into its corresponding 5-min lethal inhalation dose per gram of body weight by utilizing the Guyton equation for RV and the reported value for animal weight. This lethal dose (per grain of mouse), calculated from mouse LC99 data, agreed within 1 percent with the lethal dose (per gram of rat) calculated from our rat experiments. Obviously, the effective CO dose for 1 g of rat tissue equals the effective CO dose for 1 g of mouse tissue. We have found the same agreement between the rat data from our experiments and 5-min LC₀₉ data from the literature for rat exposures to CO.

An additional observation is even more pertinent to the task of attempting to solve human problems by doing research on nonhuman species. We found that if one converted the incapacitating CO dose for rats to the equivalent dose for a "70-kg rat," the resultant dose agreed within 0.1 percent with the dose predicted by the Peterson and Stewart equation¹³ for human acquisition of a 46.5-percent COHb saturation.*

^{*}Assuming that human incapacitation occurs when the blood COHb level reaches 46.5-percent saturation and using Guyton's constant for adult human (resting) RV of 2.06 (Wt)^{0.75}.

Evaluation of similar extrapolations for HCN, from our rat data to humans, is made difficult by the paucity of quantitative data for HCN dose-response relationships in humans. However, the lethal inhalation dose that we measure for the rat does convert to a blood cyanide concentration of 3.4 μ g/mL (assuming the HCN is distributed uniformly throughout the total body water). Forensic data for human fatalities indicate blood cyanide concentrations from 2 to 5 μ g/mL.

The dose-response relationships just discussed for CO and HCN exposures have been applied to the combustion experiments in the following manner:

If equation (D6) is rearranged to
$$C^{-1}=2.1(D)^{-1} t(Wt)^{-0.25}$$
, (D7)

and it is recognized that the effective dose, D, is a constant (the quantity of toxic gas(es) required

to produce the observed response) with the effective concentration, C, proportional to the quantity of fuel, F, that decomposed, C=kF, we can see that for all experiments in which F is kept constant:

$$t = K(Wt)^{0.25}$$
 (D8)

where $K=D(2.1 \text{ kF})^{-1}$. Therefore, for such experiments, t can be corrected from that obtained with an experimental animal of any weight to that t which would have been obtained with a standard animal weighing 200 g.


The variation in t due to different fuel quantities, F, can be similarly corrected to that value which would have resulted from a quantity of fuel equal to one gram.

Transformations, or normalizations, based on these concepts and assumptions were utilized in converting the observed data to "standard" and "loss" response times.

References

- 1. Starrett, P., E. Lopez, B. Silverman, J. Susersky, J. Logan: Feasibility and Tradeoffs of a Transport Fuselage Fire Management System, U.S. Department of Transportation, Federal Aviation Administration Technical Report No. FAA-RD-76-54, April 1976.
- 2. National Transportation Safety Board, Aircraft Accident Report: Capitol International Airways, Inc., DC-8-63F, N4909C, Anchorage, Alaska, November 27, 1970; Report No. NTSB-AAR-72-12, File No. 1-0025, 1972.
- 3. Smith, Paul W., Charles R. Crane, Donald C. Sanders, John K. Abbott, and Boyd R. Endecott: Effects of exposure to carbon monoxide and hydrogen cyanide. Symposium (March 18–20, 1974, Salt Lake City), Physiological and Toxicological Aspects of Combustion Products, Committee on Fire Research, NRC/NAS, Washington, D.C., 1976.
- 4. Sanders, D. C., C. R. Crane, P. W. Smith, J. K. Abbott, B. R. Endecott: Effects of Exposure to Carbon Monoxide and Hydrogen Cyanide, paper presented at Aerospace Medical Association Meeting, San Francisco, California, April 28–May 1, 1975.
- 5. Smith, P. W., C. R. Crane, D. Sanders, J. Abbott, B. Endecott: Material Toxicity Evaluation by Direct Animal Exposure, Proceedings of International Symposium on Toxicity and Physiology of Combustion Products, University of Utah, Salt Lake City, Utah, March 22–26, 1976.
- 6. Smith, P. W., C. R. Crane, D. C. Sanders, J. K. Abbott, B. R. Endecott: FAA Studies of the Toxicity


- of Products of Combustion, Proceedings of the First Conference and Workshop on Fire Casualties, May 28–29, 1975, Edited by B. M. Halpin; published as Applied Physics Laboratory/Johns Hopkins Report No. APL/JHU FPP B 76–1, April 1976.
- 7. Spurgeon, J.: A Preliminary Comparison of Laboratory Methods for Assigning a Relative Toxicity Ranking to Aircraft Interior Materials. Federal Aviation Administration Report No. FAA-RD-75-37, 1975.
- 8. Sarkos, C.: Measurement of Toxic Gases and Smoke from Aircraft Cabin Interior Materials Using the NBS Smoke Chamber and Colorimetric Tubes, Federal Aviation Administration Report No. FAA-RD-76-7, 1976.
- 9. Federal Aviation Regulations, Vol. III, Part 25.853, May 1, 1972.
- 10. Spurgeon, J., L. Speitel, R. Fehrer: Thermal Decomposition Products of Aircraft Interior Materials, Federal Aviation Administration Report No. FAARD-77-20, April 1977.
- 11. Spurgeon, J.: FAA, NAFEC, personal communication.
- 12. Guyton, Arthur C.: Measurement of the respiratory volumes of laboratory animals, AM. J. PHYSIOL., 150:70-77, 1947.
- 13. Peterson, Jack E. and Richard D. Stewart: Human absorption of carbon monoxide from high concentrations in air, AM. IND. HYG. ASSOC. J., 33:293-7, 1972.



- 1. Gearmotor, model 3M126, 6 rpm, 1/20 hp, Dayton Electric Mfg. Co., Chicago, Ill.
- 2. Animal Exposure Chamber.
- 3. Furnace, Type 5423IA, I300 W, Lindberg, Div. of Sola Basic Industries, Watertown, Wisc.
- 4. Electrical Outlet Strip, model 1577, Cole-Parmer Inst. Co., Chicago, III.
- 5. Speed Controller for Recirculating Blower, Stir-Pak solid state model #4556-03, Cole-Parmer Inst. Co., Chicago, III.
- 6. Furnace Temperature Controller, Type 59344, Lindberg, Div. of Sola Basic Industries, Watertown, Wisc.
- 7. Chamber Temperature Recorder, Speedomax model H, Temperature range 25-50°C, Leeds and Northrup Co., Philadelphia, Pa.


FIGURE A-1.—Animal exposure assembly.

ANIMAL EXPOSURE CHAMBER — End View



All dimensions in centimeters

ANIMAL EXPOSURE CHAMBER - Left Side View



All dimensions in centimeters

ANIMAL EXPOSURE CHAMBER — Right Side View




FIGURE A-4,—Animal exposure chamber, right side.

ANIMAL EXPOSURE CHAMBER — Top View




Figure A-5.—Animal exposure chamber, top view.

ANIMAL EXPOSURE CHAMBER — Top View Showing Blowers and Fan Installed




FIGURE A-6.—Animal exposure chamber, top view, with blower and fan installed.

DETAIL OF DEFLECTOR ASSEMBLY




Figure A-7.—Detail section, gas deflector assembly, side view.

ROTATING CAGE (SIDE)






FIGURE A-8.—Rotating cage assembly, side view.


ROTATING CAGE (END)



RECIRCULATING BLOWER ASSEMBLY



RECIRCULATING BLOWER ASSEMBLY



All dimensions in centimeters

Front

FAN ASSEMBLY






FIGURE A-12.—Fan Assembly.

MIXING BLOWER




All dimensions in centimeters

MIXING BLOWER DELIVERY TUBE (Plexiglas)



Left Side View



ECIRCULATION ASSEMBLY




Figure A-15.—Recirculation assembly.